



DECOCORK PAINT **DATASHEET**

PRODUCT CHARACTERISTICS	
Density (UNE-EN ISO 2811-1)	1,25 g/cm ³
Non-volatile matter (1h to 125°) (UNE-EN ISO 3251)	52,00 %
Non-volatile matter by volume (UNE-EN ISO 3233-3)	40,20 %
Drying time (UNE 48301) (dry film thickness: 95 µm)	Secado al tacto: 30 min. Secado total: 1h. 35 min.
Theoretical performance (R)	0,25 kg/m ² → 80 µm 0,31 kg/m ² → 100 µm
Theoretical performance (R)	5,0 m ² /l → 80 µm 4,0 m ² /l → 100 µm
pH	9±0,5

